

FINE CASTING PLASTER

Construction Materials, Fibrous and Decorative Plaster



PRODUCT DESCRIPTION

Fine Casting Plaster is an unformulated hemihydrate plaster ($\text{CaSO}_4 \cdot 1/2\text{H}_2\text{O}$) produced from naturally occurring high purity gypsum mineral. It is off-white in colour. It is used for the production of decorative fibrous plasterwork and in general casting applications. It can also be used as a filler or additive within proprietary formulations.

PRODUCT BENEFITS

- + Typical set time and working properties suitable for production of fibrous plasterwork
- + Good reproduction of fine detail
- + Unformulated high purity plaster also suitable for use within proprietary formulations

APPLICATIONS

Fibrous plaster, Floor, Wall

TECHNICAL INFORMATION

Plaster to Water Ratio

Plaster to Water Ratio (by weight)	1.43:1
------------------------------------	--------

Water to plaster ratio (by weight)	70%
-------------------------------------	-----

Chemical Properties

Chemical Composition	$\text{CaSO}_4 \cdot 1/2\text{H}_2\text{O}$
----------------------	---

Colour	white
--------	-------

Colorometer L* value	92
----------------------	----

Colorometer a* value	0.5
----------------------	-----

Colorometer b* value	3
----------------------	---

Setting Parameters

Initial setting time (minutes)	21
--------------------------------	----

Final setting time (minutes)	28
------------------------------	----

Linear Expansion (%)	0,2
----------------------	-----

Mechanical Properties

Brinell Hardness (MPa)	20
------------------------	----

Dry compressive strength (Mpa)	13
--------------------------------	----

Wet Compressive strength (Mpa)	5
--------------------------------	---

Physical Properties

Particle Size (% weight retained)	1 % at 150 μm 8 % at 90 μm 15 % at 63 μm 30 % at 32 μm
-----------------------------------	---

Loose bulk density (kg/m ³)	800
---	-----

Bulk density (compacted) kg / m ³	1200
--	------

The technical data outlined represents typical figures only. For further details, please contact Saint-Gobain Formula directly.

PACKAGING AND SHELF LIFE

	Packaging Available	Shelf Life (Month)
Bag	25 kg	3 months
Bulk Bag	1.5 T	3 months
Bulk tanker	< 30 T	Technical properties noted are at receipt of goods.

When stored under dry conditions and in its original packaging, the product will have a specified shelf life that commences from the date of manufacture that is displayed on each sack. Shelf life depends on the packaging type. For those products where a defined 'best before' date is applicable, BBE (Best Before End) followed by the date will be displayed on each sack.

CERTIFICATION



DOP n° NK001

ENVIRONMENT, HEALTH AND SAFETY

Material Safety Data Sheets of Saint-Gobain Formula plasters and gypsum minerals are available for all products and may be obtained directly on our website in the product and documentation sections. No liability is accepted by Saint-Gobain Formula for injury to any person or loss or damage to property by improper use of the product.

NOTIFICATION

The plaster to water ratios quoted are those used in Saint-Gobain Formula's standard test methods and are not necessarily those used in practice. The precise consistency to use will need to be adjusted to suit the individual application. Changes to plaster to water ratio will influence product performance, particularly setting time and strength. Unless otherwise stated, Saint-Gobain Formula's standard test methods apply. To obtain a copy of the test method, please contact Saint-Gobain Formula directly. This literature cancels and replaces any previous document. All information given is provided in good faith and may be subject to change. It's advisable to contact Saint-Gobain Formula in case of any doubt arising from the content of such information.

CONTACT

For any information, please visit our website
www.saintgobainformula.com



Sales contact



Documentation



Technical information



Global information